

**TABLE - SUMMARY OF BUILDING MATERIAL
 ANALYTICAL RESULTS**

Sample Type	Location ID	Total PCBs (mg/kg)
Interior Paint	52-ROF-TRU-001	184.7
Interior Paint	52-ROF-TRU-002	132
Interior Paint	52-ROF-TRU-003	173.8
Interior Paint	52-ROF-TRU-004	162.6
Interior Paint	52-ROF-TRU-005	75.57
Interior Paint	52-ROF-TRU-006	97.2
Interior Paint	52-ROF-TRU-007	201.2
Interior Paint	52-ROF-TRU-008	242
Interior Paint	52-ROF-TRU-009	237.6
Interior Paint	52-ROF-TRU-010	299
Interior Paint	52-WAL-INP-001	263.8
Interior Paint	52-WAL-INP-002	45.6
Interior Paint	52-WAL-INP-003	89.7
Interior Paint	52-WAL-INP-004	26.8
Interior Paint	52-WAL-INP-005	173.5
Interior Paint	52-WAL-INP-006	102.4
Interior Paint	52-WAL-INP-007	316
Interior Paint	52-WAL-INP-008	53.6
Interior Paint	52-WAL-INP-009	101.6
Interior Paint	52_WAL-PAI-001	120.6
Interior Paint	52_WAL-PAI-002	128.2
Interior Paint	52_WAL-PAI-003	144.7
Interior Paint	52_WAL-PAI-004	154.1
Interior Paint	52_WAL-PAI-005	204.7
Interior Paint	52_WAL-PAI-006	0.934
Interior Paint	52_WAL-PAI-007	204.3
Interior Paint	52_WAL-PAI-008	300.2
Interior Paint	52_WAL-PAI-010	117.8
Interior Paint	52-WAL-PAI-009	86.3

Interior CMU	52-WAL-CMU-001	0.1497
Interior CMU	52-WAL-CMU-002	ND
Interior CMU	52-WAL-CMU-003	0.785
Interior CMU	52-WAL-CMU-004	0.088
Interior Brick	52-WAL-INB-001_1	133.1
Interior Brick	52-WAL-INB-001_11	0.725
Interior Brick	52-WAL-INB-001_22	1.005
Interior Brick	52-WAL-INB-001_4	2.033
Interior Brick	52-WAL-INB-002_1	0.1663
Interior Brick	52-WAL-INB-002_11	0.103
Interior Brick	52-WAL-INB-002_22	0.321
Interior Brick	52-WAL-INB-002_4	0.0909
Interior Brick	52-WAL-INB-003_1	0.1451
Interior Brick	52-WAL-INB-003_11	0.1829
Interior Brick	52-WAL-INB-003_22	0.0788
Interior Brick	52-WAL-INB-003_4	0.1016
Interior Brick	52-WAL-INB-004_1	0.0959
Interior Brick	52-WAL-INB-004_11	1.008
Interior Brick	52-WAL-INB-004_22	0.836
Interior Brick	52-WAL-INB-004_4	0.0564
Interior Brick	52-WAL-INB-005_1	0.1228
Interior Brick	52-WAL-INB-005_11	0.592
Interior Brick	52-WAL-INB-005_22	0.78
Interior Brick	52-WAL-INB-005_4	2.326
Interior Brick	52-WAL-INB-006_1	0.0904

Notes Abbreviations:

ND: Not detected above laboratory detection limits

Sample Type	Location ID	Total PCBs (mg/kg)
Interior Brick	52-WAL-INB-006_11	0.446
Interior Brick	52-WAL-INB-006_22	0.569
Interior Brick	52-WAL-INB-006_4	0.857
Interior Brick	52-WAL-INB-007_1	ND
Interior Brick	52-WAL-INB-007_11	0.2005
Interior Brick	52-WAL-INB-007_22	ND
Interior Brick	52-WAL-INB-007_4	0.279
Interior Brick	52-WAL-INB-008_1	ND
Interior Brick	52-WAL-INB-008_11	0.219
Interior Brick	52-WAL-INB-008_22	0.2112
Interior Brick	52-WAL-INB-008_4	0.1382
Interior Brick	52-WAL-INB-009_1	0.724
Interior Brick	52-WAL-INB-009_11	ND
Interior Brick	52-WAL-INB-009_22	0.1578
Interior Brick	52-WAL-INB-009_4	0.315
Interior Brick	52-WAL-INB-010_1	1.083
Interior Brick	52-WAL-INB-010_11	0.889
Interior Brick	52-WAL-INB-010_22	0.0358
Interior Brick	52-WAL-INB-010_4	0.0289
Interior Brick	52-WAL-INB-011_1	0.26
Interior Brick	52-WAL-INB-011_11	4.02
Interior Brick	52-WAL-INB-011_22	0.1547
Interior Brick	52-WAL-INB-011_4	ND
Interior Brick	52-WAL-INB-012_1	4.8
Interior Brick	52-WAL-INB-012_11	0.519
Interior Brick	52-WAL-INB-012_22	9.79
Interior Brick	52-WAL-INB-012_4	0.1966
Interior Brick	52-WAL-INB-013_1	62.4
Interior Brick	52-WAL-INB-013_11	0.0656
Interior Brick	52-WAL-INB-013_22	0.0311
Interior Brick	52-WAL-INB-013_4	0.1099
Interior Brick	52-WAL-INB-014_1	2.383
Interior Brick	52-WAL-INB-014_11	0.942
Interior Brick	52-WAL-INB-014_22	24.6
Interior Brick	52-WAL-INB-014_4	1.3498
Interior Brick	52-WAL-INB-015_1	ND
Interior Brick	52-WAL-INB-015_11	0.911
Interior Brick	52-WAL-INB-015_22	0.0332
Interior Brick	52-WAL-INB-015_4	ND
Interior Brick	52-WAL-INB-016_1	2.505
Interior Brick	52-WAL-INB-016_11	0.369
Interior Brick	52-WAL-INB-016_22	3.89
Interior Brick	52-WAL-INB-016_4	0.2639
Interior Brick	52-WAL-INB-017_1	0.626
Interior Brick	52-WAL-INB-017_11	1.001
Interior Brick	52-WAL-INB-017_22	1.404
Interior Brick	52-WAL-INB-017_4	5.68
Interior Brick	52-WALL-INB-016-11	0.369
Interior Brick	52-WALL-INB-016-22	3.89
Floor Slab	52-FLR-CON-001	6.892
Floor Slab	52-FLR-CON-002	870
Floor Slab	52-FLR-CON-003	ND
Floor Slab	52-FLR-CON-004	49.64
Floor Slab	52-FLR-CON-005	0.05
Floor Slab	52-FLR-CON-006	0.517
Floor Slab	52-FLR-CON-007	0.0273

Notes Abbreviations:

ND: Not detected above laboratory detection limits

Sample Type	Location ID	Total PCBs (mg/kg)
Floor Slab	52-FLR-CON-008	0.249
Floor Slab	52-FLR-CON-009	21.4
Floor Slab	52-FLR-CON-010	0.0965
Floor Slab	52-FLR-CON-011	4.769
Floor Slab	52-FLR-CON-012	17.67
Floor Slab	52-FLR-CON-013	0.0457
Floor Slab	52-FLR-CON-014	0.0542
Floor Slab	52-FLR-CON-015	53.6
Floor Slab	52-FLR-CON-016	19366
Floor Slab	52-FLR-CON-017	3.497
Floor Slab	52-FLR-CON-018	0.7347
Floor Slab	52-FLR-CON-019	ND
Floor Slab	52-FLR-CON-020	ND
Floor Slab	52-FLR-CON-021	4.115
Floor Slab	52-FLR-CON-022	62.96
Floor Slab	52-FLR-CON-023	22.62
Floor Slab	52-FLR-CON-024	0.1608
Floor Slab	52-FLR-CON-025	2.52
Floor Slab	52-FLR-CON-026	15.25
Floor Slab	52-FLR-CON-027	24.41
Floor Slab	52-FLR-CON-028	16.44
Floor Slab	52-FLR-CON-029	40.85
Floor Slab	52-FLR-CON-031	45.5
Floor Slab	52-FLR-CON-032	13.5
Floor Slab	52-FLR-CON-033	19.59
Floor Slab	52-FLR-CON-034	0.692
Floor Slab	52-FLR-CON-035	14.19
Floor Slab	52-FLR-CON-036	5.427
Floor Slab	52-FLR-CON-037	8
Floor Slab	52-FLR-CON-038	2.598
Floor Slab	52-FLR-CON-030	29.1
Floor Slab	52CR-01	0.0248
Floor Slab	52CR-02	10.9
Floor Slab	52CR-03	12.7
Floor Slab	52CR-04	2.38
Floor Slab	52CR-05	16.6
Floor Slab	52CR-06	ND
Floor Slab	52CR-07	3.03
Floor Slab	52CR-08	ND
Floor Slab	52CR-09	4.7
Floor Slab	52CR-10	8.9
Floor Slab	52CR-11	1.93
Floor Slab	52CR-12	0.17
Floor Slab	52CR-13	1.38
Floor Slab	52CR-14	0.98
Floor Slab	52CR-15	2.33
Floor Slab	52-FC-1-01	74
Floor Slab	52-FC-1-02	27.2
Floor Slab	52-FC-1-03	12
Floor Slab	52-FC-1-04	11.6
Floor Slab	52-FC-1-05	11
Floor Slab	52-FC-1-06	8.3
Floor Slab	52-FC-1-07	85
Floor Slab	52-FC-1-08	12
Floor Slab	52-FC-1-09	12
Floor Slab	52-FC-1-10	35

Notes Abbreviations:

ND: Not detected above laboratory detection limits